

UH253						
MATERIAL GROUPS	8		8		8	
HRC	50~55		55~60		60~65	
N/mm ²					~	
Vc [m/min]	60~75		60~75		60~75	
Ø mm.	n	Vf	n	Vf	n	Vf
1	22280	261	22280	209	22280	209
1.5	14850	221	14850	177	14850	177
2	11140	211	11140	168	11140	168
2.5	8910	196	8910	157	8910	157
3	7430	196	7430	156	7430	156
4	5570	186	5570	149	5570	149
5	4460	181	4460	145	4460	145
6	3710	179	3710	143	3710	143
8	2790	177	2790	141	2790	141
10	2230	174	2230	139	2230	139
12	1860	172	1860	138	1860	138
C ap x p	0.05Dx0.1D		0.05Dx0.1D		0.05Dx0.1D	

